ROYALFIL OA 730 ()


Applications

Rebuilding & reclamation of chain guide rolls, wheels, worn out parts of bulldozers, shaft rollers in mining & civil engineering industries.

Characteristics on Usage

RoyalFil OA - 730 is a low alloy air hardening type self shielded fluxcored wire designed for rebuilding & reclamation of chain guide rolls, wheels, worn out parts of bulldozers, shaft rollers in Mining & Civil Engineering Industries.

Welding Positions



1G

Chemical Composition Of Weld Metal

Element	C%	Mn%	Si%	Cr %
Typical Values	0.15	1.50	0.80	1.50

Mechanical Properties Of Weld Metal

HARDNESS ON III rd LAYER

25-35 HRC

Welding Parameters (DC + VE)

Diameter	Flat & Horizontal	Flat & Horizontal
(mm)	(A)	(V)
2.40 / 2.80 mm	250-400	26-32

Packing

Drum packing in 100Kgs / 250 Kgs. .

TOP A